

High Purity Zirconia (3 mole% yttria sintering aid)

Typical Chemical Analysis

	(Weight %)
ZrO <sub>2</sub> + HfO <sub>2</sub>	94.2 +- 0.2
Y <sub>2</sub> O <sub>3</sub>	5.4 +- 0.2

	(Maximum Percent %)
Al <sub>2</sub> O <sub>3</sub>	0.30
SiO <sub>2</sub>	0.15
Fe <sub>2</sub> O <sub>3</sub>	0.01
TiO <sub>2</sub>	0.15
Na <sub>2</sub> O	0.05
CaO	0.05